

GEN 309L Welding Wire and Rod

GEN 309L is used to weld base metals of similar chemical composition in wrought or cast form. It is also suitable for joining dissimilar metals such as 18Cr-8Ni stainless steel to mild steel. The low carbon content minimizes the possibility of carbide precipitation.

CONFORMANCES

AWS A5.9/A5.9M	:	ER 309L
ASME SFA-A5.9	:	ER 309L
UNS	:	S30983

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Mn
0.03 max	23.0 – 25.0	12.0 – 14.0	0.75 max	1.0 – 2.5
0.015	23.4	13.6	0.08	1.65
%Si	%P	%S	%Cu	
0.30 – 0.65	0.03 max	0.03 max	0.75 max	
0.04	0.02	0.01	0.06	

TYPICAL WELD METAL MECHANICAL PROPERTIES

Tensile Strength	:	87,000 psi	600 MPa
Yield Strength	:	59,000 psi	406 MPa
Elongation	:	35 %	

TYPICAL WELDING PARAMETERS

Process	Diameter	Voltage	Amperage	Gas/Flux
TIG (GTAW)	.1/16"	1.6 mm	14 – 18	90 – 130
	.3/32"	2.4 mm	15 – 20	120 – 175
	.1/8"	3.2 mm	16 – 20	150 – 220
MIG (GMAW)	.035"	0.9 mm	29 - 33	160 – 180
	.045"	1.1 mm	29 – 33	180 – 220
	.063"	1.6 mm	29 – 33	210 – 250
Sub Arc (SAW)	.093"	2.4 mm	29 – 32	300 – 350
	.125"	3.2 mm	29 – 32	400 – 550
	.156"	4.0 mm	29 – 32	500 – 650

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED

BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.