

GEN 309LMO Welding Wire and Rod

GEN 309LMO is similar to ER309LMO with lower chromium and higher nickel content which is typically used to weld type 316 clad steels on the first pass in cladding steel as well as to weld dissimilar metals such as molybdenum-bearing stainless steels to carbon or low alloy steels.

CONFORMANCES

AWS A5.9/A5.9M :
ASME SFA-A5.9 :
ISO 14343-B :

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Mn
0.03 max	20.5 – 21.5	14.2 – 15.0	2.0 – 3.0	1.5 – 2.25
%Si	%P	%S	%Cu	Total Others
0.30 – 0.60	0.025 max	0.005 – 0.02	0.30 max	

TYPICAL WELD METAL MECHANICAL PROPERTIES

Yield Strength : 56,000 psi
Tensile Strength : 85,000 psi
Elongation : 35 %

TYPICAL WELDING PARAMETERS

Process	Diameter		Voltage	Amperage	Gas/Flux
TIG (GTAW)	1/16"	1.6 mm	14 – 17	90 – 130	100% Ar
	3/32"	2.4 mm	15 – 20	120 – 175	100% Ar
MIG (GMAW)	.035"	0.9 mm	29 – 33	160 – 190	98%Ar – 2%O ₂
	.045"	1.1 mm	29 – 33	180 – 220	98%Ar – 2%O ₂
Sub Arc (SAW)	.093"	2.4 mm	28 – 33	250 – 450	
	.125"	3.2 mm	29 – 34	300 – 500	

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED
BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.