

GEN 316L Welding Wire and Rod

GEN 316L shares the same characteristics as GEN 316, except for the lower carbon content. GEN 316L is primarily used for welding low-carbon molybdenum-bearing austenitic alloys. The lower carbon content reduces the possibility of intergranular chromium carbide precipitation and thus increases the resistance against intergranular corrosion.

CONFORMANCES

AWS A5.9/A5.9M	:	ER316L
ASME SFA-A5.9	:	ER316L
UNS	:	S31683

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Mn
0.03 max	18.0 – 20.0	11.0 – 14.0	2.0 – 3.0	1.0 – 2.5
0.01	18.5	12.2	2.4	1.7

%Si	%P	%S	%Cu
0.30 – 0.65	0.03 max	0.03 max	0.75 max
0.37	0.02	0.01	0.20

TYPICAL WELD METAL MECHANICAL PROPERTIES

Tensile Strength	:	86,000 psi	593 MPa
Yield Strength	:	58,000 psi	400 MPa
Elongation	:	35 %	

TYPICAL WELDING PARAMETERS

Process	Diameter		Voltage	Amperage	Gas/Flux
TIG (GTAW)	1/16"	1.6 mm	14 – 17	80 – 150	100% Ar
	3/32"	2.4 mm	15 – 20	150 – 250	100% Ar
	1/8"	3.2 mm	16 – 20	200 – 375	100% Ar
MIG (GMAW)	.035"	0.9 mm	29 - 33	160 - 180	98%Ar – 2%O ₂
	.045"	1.1 mm	29 – 33	180 - 220	
	.063"	1.6 mm	29 – 33	210 - 250	
Sub Arc (SAW)	.093"	2.4 mm	29 - 32	300 - 350	
	.125"	3.2 mm	29 - 32	400 – 550	
	.156"	4.0 mm	29 - 32	500 - 650	

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED
BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.