

GEN 420 Welding Wire and Rod

GEN 420 is generally used for surfacing applications requiring higher hardness as well as superior abrasion resistance. Pre-heat and inter-pass temperatures of not less than 400°F (204°C) followed by slow cooling is required. Post weld heat treatment is typically used to temper the weld deposit.

CONFORMANCES

AWS A5.9/A5.9M	:	ER420
ASME SFA-A5.9	:	ER420
UNS	:	S42080

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Mn
0.25 – 0.40 0.35	12.0 – 14.0 12.5	0.60 max 0.13	0.75 max 0.02	0.60 max 0.45
%Si	%P	%S	%Cu	
0.50 max 0.36	0.03 max 0.016	0.03 max 0.005	0.75 max 0.16	

TYPICAL WELD METAL MECHANICAL PROPERTIES

Tensile Strength	:	105,000 psi	723 MPa
Yield Strength	:	95,000 psi	655 MPa
Elongation	:	16 %	

TYPICAL WELDING PARAMETERS

Process	Diameter		Voltage	Amperage	Gas/Flux
TIG (GTAW)	1/16"	1.6 mm	12 – 15	80 – 150	100% Ar
	3/32"	2.4 mm	13 – 16	150 – 250	100% Ar
	1/8"	3.2 mm	14 – 17	200 – 350	100% Ar
MIG (GMAW)	.035"	0.9 mm	24 – 29	150 – 220	98%Ar – 2%O ₂
	.045"	1.1 mm	25 – 30	160 – 260	98%Ar – 2%O ₂
Sub Arc (SAW)	.093"	2.4 mm	28 – 33	250 – 450	
	.125"	3.2 mm	29 – 34	300 – 500	

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED
BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.