

GEN 430 Welding Wire and Rod

CWR-430 is a ferritic stainless steel filler metal offering good ductility in heat-treated condition. It is generally used to weld similar alloys but can also be used for overlays and thermal spraying. Pre-heating and post weld heat treatment is required to obtain optimum mechanical properties and corrosion resistance.

CONFORMANCES

AWS A5.9/A5.9M	:	ER430
ASME SFA-A5.9	:	ER430
UNS	:	S43080

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Mn
0.10 max 0.025	15.5 – 17.0 16.13	0.60 max 0.32	0.75 max 0.055	0.60 max 0.37
%Si	%P	%S	%Cu	
0.50 max 0.28	0.03 max 0.023	0.03 max 0.004	0.75 max 0.23	

TYPICAL WELD METAL MECHANICAL PROPERTIES

Tensile Strength	:	77,500 psi	534 MPa
Yield Strength	:	59,000 psi	407 MPa
Elongation	:	25 %	

TYPICAL WELDING PARAMETERS

Process	Diameter		Voltage	Amperage	Gas/Flux
TIG (GTAW)	1/16"	1.6 mm	14 – 17	90 – 130	100% Ar
	3/32"	2.4 mm	15 – 20	125 – 175	100% Ar
MIG (GMAW)	.035"	0.9 mm	29 – 33	160 – 180	98%Ar – 2%O ₂
	.045"	1.1 mm	29 – 33	180 – 220	98%Ar – 2%O ₂
Sub Arc (SAW)	.093"	2.4 mm	28 – 33	250 – 450	
	.125"	3.2 mm	29 – 34	300 – 500	

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED
BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.