

GEN 430LNb Welding Wire and Rod

GEN 430LNb is a stabilized ferritic stainless steel filler metal offering superior mechanical properties to GEN 430. Due to its excellent fatigue resistance, GEN 430LNb is often used in automotive industry.

CONFORMANCES

AWS A5.9	:	ER430LNb
ASME SFA-5.9	:	ER430LNb
UNS	:	--

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Mn	Nb
0.03 max	15.5 – 17.0	0.60 max	0.75 max	0.60 max	8xC to 1.2
%Si	%P	%S	%Cu	Total Others	
0.50 max	0.03 max	0.03 max	0.75 max	0.50 max	

TYPICAL WELD METAL MECHANICAL PROPERTIES

Tensile Strength	:	74,000 psi	510 MPa
Yield Strength	:	60,000 psi	413 MPa
Elongation	:	25 %	

TYPICAL WELDING PARAMETERS

Process	Diameter		Voltage	Amperage	Gas/Flux
TIG (GTAW)	1/16"	1.6 mm	14 – 17	90 – 130	100% Ar
	3/32"	2.4 mm	15 – 20	125 – 175	100% Ar
MIG (GMAW)	.035"	0.9 mm	28 – 33	160 – 180	98%Ar – 2%O ₂
	.045"	1.1 mm	28 – 33	170 – 190	98%Ar – 2%O ₂
	.062"	1.6 mm	28 – 33	190 – 210	

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED
BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.