

GEN 630 Welding Wire and Rod

GEN 630 is designed primarily for welding ASTM A564 Type 630 (17-4PH) and other similar precipitation-hardening stainless steel. The chemical composition is modified to minimize the presence of ferrite networks in the martensitic microstructure which has a significant effect on mechanical properties.

CONFORMANCES

AWS A5.9/A5.9M	:	ER630
ASME SFA-A5.9	:	ER630
UNS	:	S17480

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Mn
0.05 max 0.02	16.0 – 16.75 15.6	4.5 – 5.0 4.6	0.75 max 0.13	0.25 – 0.75 0.70
%Si	%P	%S	%Cu	Nb+Ta
0.75 max 0.42	0.03 max 0.02	0.03 max 0.02	3.25 – 4.00 3.30	0.15 – 0.30 0.25

TYPICAL WELD METAL MECHANICAL PROPERTIES

Tensile Strength	:	150,000 psi	1034 MPa
Yield Strength	:	135,000 psi	930 MPa
Elongation	:	10 %	

TYPICAL WELDING PARAMETERS

Process	Diameter		Voltage	Amperage	Gas/Flux
TIG (GTAW)	1/16"	1.6 mm	14 – 16	90 – 140	100% Ar
	3/32"	2.4 mm	15 – 20	120 – 175	100% Ar
	1/8"	3.2 mm	16 – 20	180 – 300	100% Ar
MIG (GMAW)	.035"	0.9 mm	23 – 29	170 – 300	98%Ar – 2%O ₂
	.045"	1.1 mm	24 – 30	190 – 360	98%Ar – 2%O ₂
Sub Arc (SAW)	.093"	2.4 mm	28 – 32	250 – 450	
	.125"	3.2 mm	29 – 34	300 – 500	

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED
BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.