

GEN 825 Welding Wire and Rod

GEN 825 is used for welding of nickel-iron-chromium-molybdenum-copper alloys. It can also be used for overlay cladding where similar chemical composition is required.

CONFORMANCES

AWS A5.14	:	ERNiFeCr-1
ASME SFA-5.14	:	ERNiFeCr-1
UNS	:	N08065

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Ti	%Fe	%Mn
0.05 max. 0.01	19.5 – 23.5 21.5	38.0 – 46.0 39.5	2.5 – 3.5 3.10	0.60 – 1.20 0.85	22.0 min. 32.7	1.0 max. 0.50
%Si	%P	%S	%Cu	%Al	Total Others	
0.50 max. 0.25	0.03 max. 0.015	0.03 max. 0.002	1.5 – 3.0 1.9	0.20 max. 0.14	0.50 max.	

TYPICAL WELD METAL MECHANICAL PROPERTIES

Tensile Strength	:	88,000 psi	607 MPa
Yield Strength	:	61,000 psi	420 MPa
Elongation	:	34 %	

TYPICAL WELDING PARAMETERS*

Process	Diameter		Voltage	Amperage	Gas/Flux
TIG (GTAW)	.093"	2.4 mm	Direct Current		100% Ar
MIG (GMAW)	.035"	0.9 mm	29 – 33	160 – 190	75% Ar – 25% He
	.045"	1.1 mm	29 – 33	180 – 220	75% Ar – 25% He
	.062"	1.6 mm	29 – 33	210 – 250	75% Ar – 25% He
Sub Arc (SAW)	.093"	2.4 mm	29 – 32	300 – 350	
	.125"	3.2 mm	29 – 32	400 – 550	

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED
BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.